



Advanced Materials

Epoxy resins & hardeners

Selector guide

Epoxy resins

Hardeners

Accelerators

Additives

Waterborne system



Epoxy resins	P.1-3
Hardeners	P.4-5
Accelerators	P.6
Additives	P.6
Waterborne system	P.7

About Huntsman

Huntsman is a global manufacturer and marketer of differentiated chemicals. Its operating companies manufacture products for a variety of global industries, including chemicals, plastics, automotive, aviation, textiles, footwear, paints and coatings, construction, technology, agriculture, health care, detergent, personal care, furniture, appliances and packaging. Originally known for pioneering innovations in packaging and, later, for rapid and integrated growth in petrochemicals, Huntsman today has more than 12,000 employees and operates from multiple locations worldwide. The Company had 2011 revenues of over \$11 billion.

Advanced Materials

Epoxy resins

Basic liquid epoxy resins • Araldite® / Tactix® / Quatrex®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Flash point [°C]	Comments/Applications
GY 250	5.30-5.45	183-189	10,000-12,000	≤2	≥200	General purpose high viscosity unmodified basic liquid epoxy resin based on bisphenol-A.
GY 9708-3	5.20-5.50	182-192	11,000-14,000	≤1	≥200	General purpose high viscosity unmodified basic liquid epoxy resin based on bisphenol-A.
GY 6010	5.20-5.50	182-192	11,000-14,000	≤1	≥200	General purpose high viscosity unmodified basic liquid epoxy resin based on bisphenol-A.
GY 280	3.57-4.45	225-280	450-700 ¹⁾	≤3 ¹⁾	≥100	Semi-solid epoxy resin based on bisphenol-A for high solid corrosion protective coatings.
GY 2600	5.29-5.43	185-189	12,000-14,000	≤2	≥200	High purity bisphenol-A based epoxy resin for CED application, low hydrolyzable chlorine content (200-300 ppm).
Quatrex® 1010	5.26-5.50	182-190	11,000-14,000	-	-	High purity bisphenol-A based epoxy resin, very low hydrolyzable chlorine content (< 200 ppm).
MY 790-1	5.70-5.90	169-175	4,000-5,500	-	>200	High purity bisphenol-A based epoxy resin, extremely low total chlorine content (about 700 ppm) and hydrolyzable chlorine content (< 200 ppm).
Tactix®123	5.68-5.80	172-176	4,400-5,600	-	-	Very low viscosity bisphenol-A based epoxy resin for applications such as filament winding.
CY 179	7.0-7.6	131-143	350-450	≤1	118	Low viscosity cycloaliphatic epoxy resin for outdoor applications.
CY 184	5.80-6.10	164-173	700-900	-	≥169	Low viscosity cycloaliphatic epoxy resin for outdoor applications.

1) being semi-solid, this is determined with a 70% solution in butylcarbitol

Basic solid epoxy resins • Araldite®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Softening point [°C]	Comments/Applications
GT 7071	1.90-2.00	500-525	200-250	≤1	77-82	Standard basic type-1 resin for corrosion protective coatings.
GT 7072	1.68-1.75	570-595	280-340	≤1	82-90	Standard basic type-2 resin for high flow powder coating or corrosion protective coatings.
GT 7004	1.33-1.40	715-750	500-600	≤1	95-101	General purpose type 3½ epoxy resin for hybrid and straight epoxy powder coatings with high storage stability and good overall properties.
GT 6084-2	1.12-1.20	833-890	550-700	≤2	99-105	Type 4 epoxy resin for functional applications, with outstanding flexibility and storage stability. In very hot climates, improving the storage stability of decorative powder coatings.
GT 6097	0.53-0.59	1,695-1,885	1,800-2,600	≤1	120-132	Standard type 7 epoxy resin for packaging and coil coating application when combined with phenol-formaldehyde or amino resins. Coatings show excellent chemical resistance and flexibility.
GT 6099	0.34-0.42	2,380-2,940	5,000-10,000	≤2	143-158	Standard type 9 epoxy resin with better flexibility than Araldite® GT 6097.
GT 6609	0.34-0.42	2,380-2,940	3,500-5,500	≤1	~150	Similar to Araldite® GT 6099 adhesives with greatly reduced viscosity.
GT 6610	0.26-0.34	2,940-3,846	5,000-8,000	≤2	~150	Similar to Araldite® GT 6099 adhesives, ideal for more flexible and higher viscous lacquers.
GT 7220	1.83-1.93	518-546	460-670	≤2	-95	Type 4 solid epoxy resin modified with epoxy phenol novolac high reactivity, medium melt viscosity with low temperature curing capabilities. Improves thermal and chemical resistance over conventional epoxy resins.
GT 7255	1.17-1.29	775-855	1,430-1,850	≤1	106-113	Type 7 solid epoxy resin modified with epoxy phenol novolac, for powder coatings showing good chemical resistance and mechanical performances.
GT 6450	1.37-1.56	640-730	350-500	≤2	91-94	Type 2½ epoxy resin based on Araldite® GT 6063 resin modified with 2% flow agent. For the formulation of hybrids with excellent flow and good storage stability. Type 2½ epoxy resin based on Araldite® GT resin 6063 modified with 2% flow agent. For the formulation of hybrids with excellent flow and good storage stability.

1) 40% solution in butylcarbitol

Basic epoxy resin solutions • Araldite®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Solids [°C]	Comments/Applications
GZ 280 X 80	3.10-3.40	290-323	600-850	≤3	79.0-81.0	Araldite® GY 280 resin in xylene.
GZ 290 X 90	3.30-3.70	270-305	1,300-3,700	≤6	89.0-91.0	Modified semi-solid resin in xylene for high solid content coatings in ship-building, maintenance, and anti-corrosion protection.
GZ 7071 X 75	1.50-1.67	600-670	7,000-10,000	≤2	74.0-76.0	Araldite® GT 7071 resin in xylene.
GZ 7488 V 40	≤0.06	≥17,000	3,000-6,000	≤4	39.0-41.0	Epoxy resin solution with high molecular weight, mainly with amino and phenolformaldehyde resins for very flexible coil primers and to flexibilise can coatings.
GZ 7488 N 50	≤0.08	≥12,500	2,000-5,000	≤4	49.0-51.0	Similar to Araldite® GZ 7488 V 40 resin but dissolved in MEK/cyclohexanon. Due to the MEK, preferably for ambient curing corrosion protection.

Advanced Materials

Epoxy resins

Premium resins • Araldite®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Flash point [°C]	Comments/Applications
---------	---------------------	---------------------	---------------------------	------------------	------------------	-----------------------

Bisphenol F and A/V pure • Araldite®

GY 281	5.80-6.30	158-172	5,000-7,000	<4	≥200	Unmodified, bis F epoxy for coating, adhesives, composites and casting.
GY 282	5.80-6.10	164-172	3,000-4,000	<5	≥200	Low viscosity bis F epoxy for coating, adhesives, composites and casting.
GY 285	5.80-6.10	164-173	2,000-3,000	<5	≥200	Very low viscosity bis F epoxy for coating, adhesives, composites and casting.
PY 302-2	5.65-5.90	169-177	6,500-8,000	<3	≥200	BPA/BPF resin, absolutely no crystallization.
PY 304	5.50-5.80	172-182	6,500-8,000	<3	≥200	BPA/BPF resin, extremely low crystallization tendency.
PY 306	6.00-6.40	6.00-6.40	1,200-1,600	-	≥200	High purity, very low viscosity bis F epoxy for coating, adhesives, composites and casting.

Bisphenol F and A/V with reactive diluent • Araldite®

GY 191	4.95-5.25	190-208	500-1,000	≤3	≥155	For solvent free coatings, mortars and injection system.
GY 253	5.40-5.80	172-185	800-1,300	≤2	≥145	For solvent free coatings, mortars and injection system.
GY 257	5.20-5.50	182-192	500-650	≤3	≥120	Good chemical resistance to acid but less resistant to solvents.
GY 298	2.20-2.50	400-455	2,000-4,000	≤2	≥188	High flexibility, nearly non-crystallizing.
GY 776	5.10-5.40	185-196	2,700-3,800	≤2	≥190	For solvent free coatings, dispersion coatings and adhesives.
GY 783	5.10-5.40	185-196	800-1,100	≤2	≥130	For floorings and mortars application, flexibilizing.

Toughened/Flexibilized Resins • Araldite®

GY 298	2.20-2.50	400-455	2,000-4,000	≤2	≥188	High flexibility, nearly non-crystallizing.
XU 3508	4.85-5.20	191-206	11,000-13,000	-	-	Liquid toughened epoxy resin based on bisphenol A for filament winding, pultrusion and adhesive applications.
DY 965	-	1.00-1.15 ²⁾	440-1,280 ³⁾	-	≥200	Polyurethane polyol for high impact resistance epoxy resin for improving adhesion to metals and for dust-free electronics.
LT 1522	0.55-0.64	1,562-1,820	-	-	-	Type-4 epoxy resin modified with CTBN copolymer for adhesives, composites and powder coating.
Tactix® 695	2.4-3.0	335-410	1,500-5,500 ³⁾	-	325	Single phase toughened epoxy.

1) 70°C; 2) OH+ Equiv. [eq/kg]; 3) 40°C, Pas

Reactive Diluents • Araldite®

DY-C	5.60-6.00	167-179	60-90	≤2	≥130	Diglycidylether of cyclohexane dimethanol.
DY-E	3.05-3.35	299-328	4-12	≤2	≥155	Monoglycidylether of C12-C14 alcohol.
DY-D	8.00-8.50	118-125	15-25	≤2	≥156	Diglycidylether of butanediol.
DY-F	1.95-2.35	425-513	60-90	≤3	≥130	Diglycidylether of polyoxypropylene glycol.
DY-H	6.25-6.65	150-160	21-31	≤2	≥150	Diglycidylether of 1.6-hexanediol.
DY-K	5.30-5.70	175-189	6-12	≤2	≥125	Monoglycidylether of cresol.
DY-L	1.48-1.80	556-714	140-200	≤5	≥130	Triglycidylether of polyoxypropylene glycol.
DY-P	4.30-4.70	213-233	20-28	≤3	≥135	Monoglycidylether of p-tert. butylphenol.
DY-T	7.00-9.00	111-143	100-200	≤3	≥100	Triglycidylether of trimethylpropane.
DY 3601	2.47-2.60	385-405	42-52	≤3	≥183	Diglycidylether of polyoxypropylene glycol.
DY-CNO	1.70-2.40	425-575	30-70	≤13	≥200	Monoglycidylether of cashew nut shell liquid.

Advanced Materials

Epoxy resins

Multifunctional resins • Araldite® / Tactix®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Tg [DMA] ¹⁾ [°C]	Comments/Applications
---------	---------------------	---------------------	---------------------------	------------------	-----------------------------	-----------------------

Epoxy Phenol Novolacs (EPN) • Araldite®

PY 307-1	5.60-5.90	165-179	30,000-50,000	≤4	-	Lowest viscosity, pure EPN, functionality 2.2 for solvent free or high solid content coatings with high chemical resistance.
EPN 1179	5.60-5.80	172-179	1,100-1,700 ²⁾	≤3	200	Semi-solid EPN, functionality 2.5 for solvent free or high solid content coatings with high chemical resistance.
EPN 1138	5.50-5.70	175-182	20,000-50,000 ³⁾	≤2	200	Semi-solid EPN, functionality 3.6 for solvent free or high solid content coatings with high chemical resistance.
EPN 1183	6.30-6.90	145-159	7,000-11,000	≤3	-	Medium viscosity, modified EPN, functionality 3.3. Used for coatings with high fuel resistance (with Aradur® 2973 hardener).
GY 289	5.70-6.00	167-175	7,000-11,000	≤5	-	Low viscosity EPN, functionality 2.3. It's suitable for coatings coming into contact with foodstuffs according to FDA regulation 21 CFR 175.300.

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Solids [°C]	Comments/Applications
---------	---------------------	---------------------	---------------------------	------------------	-------------	-----------------------

Epoxy Phenol Novolacs (EPN) solution • Araldite®

EPN 1180 X 80	4.40-4.56	219-227	1,200-2,000	≤2	79.0-81.0	Araldite® EPN 1138 resin in xylene.
---------------	-----------	---------	-------------	----	-----------	-------------------------------------

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Softening point [Gardner]	Tg [DMA] ¹⁾ [°C]	Comments/Applications
---------	---------------------	---------------------	---------------------------	---------------------------	-----------------------------	-----------------------

Epoxy Cresol Novolacs (ECN) • Araldite®

ECN 1273	4.30-4.60	217-233	-	68-78	200	ECN with functionality 4.8. For high temperature adhesives, electrical and laminating product areas.
ECN 1280	4.30-4.70	212-233	-	78-85	200	ECN with functionality 5.1. For high temperature adhesives, electrical and laminating product areas.
ECN 1299	4.10-4.60	217-244	7,000-15,000 ⁷⁾	85-100	200	ECN with functionality 5.4. Highest melting ECN.
ECN 9511	4.40-5.00	200-227	-	32-42	-	ECN with functionality 2.7.
ECN 9699	4.30-4.70	213-233	7,000-10,000	80-100	-	ECN with high functionality (~5.5) as modifier in combination with standard epoxy resins or other multifunctional epoxy resins such as Araldite® GT 7220 resin and Araldite® GT 7255 resin for coatings showing very high chemical – and excellent temperature resistance.

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Softening point [°C]	Tg [DMA] ¹⁾ [°C]	Comments/Applications
---------	---------------------	---------------------	---------------------------	----------------------	-----------------------------	-----------------------

Other multifunctional resins • Araldite® / Tactix®

MY 0500	8.6-9.5	105-115	2,000-5,000	-	250	Trifunctional low viscosity epoxy resin. Used for rapid cure adhesives, laminates, etc., having exceptional high heat deflection temperature.
MY 0510	9.3-10.5	95-107	550-850	-	250	High purity MY 0500. Improved stability.
MY 0600	9.2-9.8	102-109	6,000-11,000	-	250	High Tg low viscosity resin can be used for adjustments of multifunctional resin formulations, or to help the blending of tougheners. Also are frequently used in adhesive formulations to upgrade thermal performance of liquid epoxy resins.
MY 720	7.5-8.5	117-134	8,000-18,000 ³⁾	-	250	Tetra-functional liquid epoxy resin. Excellent high temperature, chemical and radiation resistance. Used for high performance composites, adhesives, laminates and high-energy radiation resistant components. Suitable for continuous use in moist environment up to 120°C.
MY 721	8.6-9.1	109-115	3,600-5,000 ³⁾	-	250	Lowest viscosity, tetra-functional epoxy resin with the same chemistry as MY 720.
XB 9721	8.6-9.1	109-115	3,600-5,000 ³⁾	-	250	Industrial grade MY 721.
MY 9512	7.5-8.5	117-134	11,000-13,000 ³⁾	-	250	Narrow viscosity of tetra-functional epoxy resin with the same chemistry as MY 720.
MY 9612	7.5-8.5	117-134	10,000-12,000 ³⁾	-	250	Narrow viscosity of tetra-functional epoxy resin with the same chemistry as MY 720.
MY 9634	7.5-8.5	117-134	13,000-15,000 ³⁾	-	250	Narrow viscosity of tetra-functional epoxy resin with the same chemistry as MY 720.
MY 9655	7.5-8.5	117-134	7,000-10,000 ³⁾	-	250	Narrow viscosity of tetra-functional epoxy resin with the same chemistry as MY 720.
MY 9663	7.4-8.6	115-135	17,000-19,000 ³⁾	-	250	Narrow viscosity of tetra-functional epoxy resin with the same chemistry as MY 720.
Tactix® 556	4.2-4.6	215-235	1,000-1,500 ⁴⁾	~53	235	Dicyclopentadiene based epoxy. Very low moisture pickup. Recommended for adhesives and composites used at elevated temperatures in a moist environment.
Tactix® 742	5.9-6.7	150-170	25-60 ⁶⁾	~49	325	Trifunctional epoxy with excellent Tg and thermal stability in the cured state.
Tactix® 756	3.7-4.1	245-265	-	77-87	-	Hydrocarbon epoxy novolac resin with lower moisture absorption. Recommended for adhesives and composites used at elevated temperatures in a moist environment.

1) when cured with Aradur® 976-1; 2) 52°C; 3) 50°C; 4) 85°C; 5) 70°C; 6) 150°C; 7) 40% solution in butylcarbitol

Special resins • Rhodofal®

Polyamide-imide (PAI) • Rhodofal®

Product	Viscosity at 25°C [mPa s]	Solids [%]	Solvent	Tg [DMA] ¹⁾ [°C]	Relative thermal stability	Comments/Applications
Rhodofal® 311	2,500-4,000	23-25	NMP/Xylene	280	•••	high temperature impregnation varnishes.

Advanced Materials

Hardeners

Basic liquid epoxy resins • Aradur®

Product	Viscosity at 25°C [mPa s]	Amine value [mg KOH/g]	Colour [Gardner]	H+ Equivalent [g/Eq]	Typical mix ratio [g/100g GY 250]	Gel time ¹⁾ [min]	Comments/Applications
---------	---------------------------	------------------------	------------------	----------------------	-----------------------------------	------------------------------	-----------------------

Polyamine based hardeners • Aradur®

Aradur® 14	400-600	350-390	≤5	75	40	17	Low moisture-sensitivity, high reactivity. Used for solvent free coating, flooring and mortar. Suitability for use with drink water systems.
Aradur® 3275	200-300	100-170	≤6	250	129 ⁷⁾	86 ⁸⁾	Nonylphenol-free. Highly flexible, even down to -10 °C. Distinctly lower viscosity than Aradur® 75 hardener and even than Aradur® 76 hardener. For the production of nonylphenol-free viscoplastic binder systems, impact-elastic coatings, crack-covering membranes and liquid foils for sealing purposes.
Aradur® 835	600-1,200 ⁹⁾	180-210	≤5	200	115	>1,200 ²⁾	For absolutely non-blush solvent based coatings. FDA-and BGA approved for contact to foodstuffs.
Aradur® 837	2,900-3,600	395-415	≤2	66	35	15	High reactivity, speeds slow hardeners with no negative effect. Tackyness can be eliminated by formulation.
Aradur® 847	150-300	350-375	≤2	75	40	30	For solvent free coatings for lining containers in contact with potable water and non-fatty food.
Aradur® 3484	300-550	350-450	≤6	95	50	30	All purpose hardener for SL flooring applications, good abrasion resistance. Recommended with Araldite® PY 3483 resin.
Aradur® 2863-1	50-250	-	≤18	6-38	3-20 ⁷⁾	-	Liquid, solvent-free, latent, warm-curing catalytically active hardener.
Aradur® 943	3,400-5,000	730-840	≤5	38	20	10	For the formulation of solvent free coatings with good resistance to alcohols. Tackyness can be eliminated by formulation.
Aradur® 956-2	290-500	1,020-1,080	≤4	47	25	35	Low viscosity amine adduct, light colored, very reactive. For room temperature curing adhesives.
Aradur® 2958	190-250	954-999	≤7	33	18	8	Very fast curing, for mortar, adhesives and chemically resistant solvent free coatings.
Aradur® 2963	30-70	325-350	≤2	85	45	40	Very low viscosity, formulated light-coloured hardener for self levelling floorings and mortar (phenol-free).
Aradur® 2965	100-300	300-325	≤4	94	50	35	Very low viscosity hardener for self levelling floorings and mortar. Good cure down to 5°C. Lowest tendency to waterspotting.
Aradur® 2973	900-1,400	300-335	≤7	85	45	35	Possible replacement of aromatic amines. Same blush free cure. Higher flexibility and resistance to inorganic acids, lower resistance to organic acids. With EPN 1183 very good fuel resistance.
Aradur® 2992	10-20	575-605	≤2	55	30	5	Very fast curing, for adhesives repair mortars and injection systems used with BY 158 or GY 783.
Aradur® 3224	30-90	300-320	≤1	~76	40	130	Very low viscosity and low reactivity hardener for self levelling floorings and mortar. Suitable for hot countries or extending gel time of other fast amine hardeners.
Aradur® 3225	150-250	310-340	≤2	~75	40	48	Medium reactivity as general purpose grade hardener for self-levelling flooring. Outstanding resistance to amine blushing and water spots.
Aradur® 3226	160-240	320-350	≤2	~76	40	25	Fast curing for winter application or to speed up other slow amine hardeners for self-levelling flooring. Very good surface aspect, excellent resistance to amine blushing and water spots.
Aradur® 3233	130-190	300-340	≤1	~75	40	50	Very light colour and excellent yellowing resistance. Outstanding resistance to amine blushing and water spots. Suitable for colour stone floors, handicraft products, adhesives and insulation materials.
Aradur® 3229	165-210	460-500	≤1	~80	40	~9	Very fast curing for winter application or to speed up other slow amine hardeners for self-levelling flooring.
Aradur® 265-1	2,700-10,000	-	≤10	94	50	49 ⁹⁾	Exceptional resistance to H2SO4 (96-98%) used with EPN 1138 .

Aromatic amine based hardeners • Aradur®

Aradur® 830	3,800-5,800	260-285	≤10	114	60	>300	With Aradur® 850 hardener for solvent free coatings or adhesives with high chemical resistance (organic acids). Extremely long pot life. Absolutely no blushing.
Aradur® 850	15,000-21,000	245-270	≤12	120	65	15	With Aradur® 830 hardener for solvent free coatings or adhesives with high chemical resistance (organic acids). Extremely long pot life. Absolutely no blushing.
Aradur® 2969	700-900	260-280	≤12	114	60	90	For solvent free coatings with high chemical resistance (organic acids and also fuels). Absolutely no blushing.
Aradur® 863 XW 80	9,000-11,000	300-345	≤12	96	51	412	For solvent based and high solid coatings. Absolutely no blushing, very high resistance to organic acids. With Aradur® 943 hardener or Aradur® 22 hardener to resist even crude methanol.

Phenalkamine • Aradur®

Aradur® 3440	1,000-3,000	475-505	≤17	~80	43	35	For fast-curing solvent-free anticorrosion coatings. Can blush.
Aradur® 3441	10,000-50,000	290-325	≤17	~130	80	60	For fast-curing solvent-based or HS marine coatings. Low blush. To make no-blush adducts.
Aradur® 3442	1,000-5,000	320-350	≤17	~125	60	35	Low-viscous version of Aradur® 3441 hardener.
Aradur® 3460	2,000-5,000	305-335	≤17	120	65	-	For high solids and solvent-free marine coatings down to 0°C. Non-blush under difficult conditions. (Ballast-tank coating in winter.)
Aradur® 3467 XW 70	1,000-3,000	170-210	≤18	180-220	-	120	Phenalkamine adduct for fast-curing solvent-based or high solids marine coatings.

Pure Amine • Aradur®

Aradur® 21	≤10	680-720	≤1	40	21	60	Aliphatic polyamine. Mostly in formulated form for solvent-free coatings, solvent-free self-levelling floorings and mortars.
Aradur® 22	≤8	810-830	≤2	34	18	60	Aliphatic polyamine. Mostly in formulated form for solvent-free coatings, solvent-free self-levelling floorings and mortars.
Aradur® 40	80-100	460-480	≤1	60	31	450	Cycloaliphatic polyamine. Mostly in formulated form for solvent-free coatings, solvent-free self-levelling floorings and mortars.
Aradur® 42	10-20	645-665	≤1	42	22	120	Cycloaliphatic polyamine. Mostly in formulated form for solvent-free coatings, solvent-free self-levelling floorings and mortars.

Advanced Materials

Hardeners

Product	Viscosity at 25°C [mPa s]	Amine value [mg KOH/g]	Colour [Gardner]	H+ Equivalent [g/Eq]	Typical mix ratio [g/100g]	Gel time ¹⁾ [min]	Comments/Applications
Polyamidoamine • Aradur®							
Aradur® 100	700-1,100 ¹⁾	83-93	≤10	-475	100	>1000 ²⁾	Semi-solid PAA. For solvent based coatings and as additive for hot melts.
Aradur® 115	3,100-3,700 ³⁾	240-260	≤10	-240	50	>1000 ²⁾	Very high viscosity. The standard product for solvent based coatings, reactive adhesives. Optimal salt spray resistance.
Aradur® 125	700-900 ⁴⁾	340-370	≤10	-130	65	120	For reactive adhesives. solvent based coatings, mastics.
Aradur® 140	300-600 ⁵⁾	370-410	≤10	-95	50	120	For reactive adhesives, castings, heat-resistant mortars.
Aradur® 145	2,400-4,000	380-420	≤10	-95	50	180	Coatings, mastics, mortars, adhesives, castings. Similar to Aradur® 140 hardener, but lower viscous.
Aradur® 250	400-700	425-455	≤8	-95	50	60	Low viscosity PAA for mortars, adhesives, mastics.
Aradur® 350	100-400	370-410	≤10	-95	50	180	Mortars, castings. Long pot life, good physical properties.
Aradur® 370	150-350	480-520	≤10	-95	50	70	Mortars, castings and adhesives.
Aradur® 450	1,000-2,000	250-290	≤10	115	60	60	Outstanding adhesion to wet concrete. Suitable for concrete primers, high solids coatings for corrosion protection under severe conditions and marine maintenance.
Aradur® 450S	600-1,400	270-310	≤10	115	60	36	Faster version of Aradur® 450 hardener
Aradur® 955	500-900	520-580	≤12	65	35	30	With Araldite® BY 157 resin for mat, self-levelling floorings.

Polyamidoamine and polyamine based hardeners solutions • Aradur®

Product	Viscosity at 25°C [mPa s]	Amine value [mg KOH/g]	Colour [Gardner]	H+ Equivalent [g/Eq]	Typical mix ratio [g/100g]	Solids [%]	Comments/Applications
Aradur® 100 X 60	2,100-3,500	49-57	≤10	-790	166 ²⁾	59-61	60% Aradur® 100 hardener solution in xylene.
Aradur® 115 X 70	750-1,250	168-182	≤10	-340	70 ³⁾	69-71	70% Aradur® 115 hardener solution in xylene.
Aradur® 422 XW 70	6,000-12,000	140-170	≤10	-340	70 ³⁾	69-71	Polyamidoamine adduct in xylene/n-butanol (3:2). Tack-free cure up to 70% humidity.
Aradur® 423 XW 60	800-1,400	122-138	≤10	-520	110 ²⁾	59-61	Polyamidoamine adduct in xylene/n-butanol (4:1). Tack-free cure up to 80% humidity.
Aradur® 424 XW 50	600-2,400	80-110	≤10	-785	165 ²⁾	49-51	Polyamidoamine adduct in xylene/n-butanol (4:1). Tack-free cure up to 100% humidity.
Aradur® 460 J 90	2,500-5,500	240-270	≤10	190	100	82-84	For high solid coatings, mortars, concrete adhesives, extreme humidity, underwater coatings.
Aradur® 30 XWM 55	2,000-2,800	104-120	≤8	-370	74 ⁴⁾	54-56	Non-blush solvent based coatings. Fast cure, good chemical resistance, particularly with EPN resins. FDA/BGA approved for food contact.
Aradur® 3776 XW 55	1,500-2,500	100-120	≤8	350	185	54-56	Similar to Aradur® 30 XWM 55 BD, but no methoxypropanol. It is Aradur® 835 hardener in solution. Free amine content < 0.9%.

1) Tecam 250g GY 250 at 23°C; 2) with GT 7071; 3) 30% xylene/n-butanol (1:1) solution; 4) 150°C; 5) 75°C; 6) 110g GY 6010 at 23°C; 7) with GY 783; 8) Tecam 250g GY 783 at 23°C

Latent hardeners • Aradur®

Product	Supply form	Mean particle size [µm]	Softening point [°C]	H+ Equivalent [g/Eq]	Gel time ¹⁾ [min]	Comments/Applications
Aradur® 2844	Powder	<75	139-143 ²⁾	37	10 ³⁾	Dicyandiamide derivative with good solubility in epoxy resins providing excellent transparency in clear coats. Outstanding flow, high gloss, good mechanical strength and good chemical resistance.
Aradur® 3082	Granulate	-	73-83	230-250	73 sec ⁴⁾	Suitable for low temperature and rapid (at high temperature) curing powder coatings with good flow, high solvent, chemical and corrosion resistance.
XB 3086	Flakes	-	84-94	-	48 sec ⁵⁾	Used to formulate low bake (approx. 120°C), fast curing powder coatings.
Aradur® 3088	Coarse powder	-	85-105 ²⁾	-	41 sec ⁶⁾	Solid epoxy amine adduct with high reactivity. Used as an accelerator and a co-hardener for epoxy powder coatings.
Aradur® 3261-1	Granulate	-	90-100	-	50 sec ⁵⁾	Solid epoxy amine adduct with high reactivity designed for low temperature (<150°C) cure of epoxy powder coatings.
Aradur® 9690	Flakes	-	100-105	~ 115	-	Cresol novolac hardener used in combination with multifunctional epoxies such as Araldite® ECN 1299 resin for the formulation of high temperature and chemical resistant powder coatings.
Aradur® 9506	Powder	-	90-100	35	10	Modified polyamide hardener. Excellent shelf life with a six month latency at room temperature. Excellent adhesion, good mechanical, highly reactive at 100°C. Suitable for one part adhesive, tooling, vinyl plastisols, dipping compounds.
Aradur® 9664-1	Tan colored powder	<64	174-178	63	180	Micropulverized 4,4'-DDS. Excellent high temperature and chemical resistance. Suitable for adhesives, prepreps, composites and PWB laminates.
Aradur® 9719-1	White to off-white powder	<60	165-175	63	-	Micropulverized 3,3'-DDS. Excellent high temperature and chemical resistance. Suitable for adhesives, prepreps, composites and PWB laminates.
Aradur® 5200	Clear, brown liquid	-	-	45	480 ⁷⁾	Low viscosity liquid aromatic amine for adhesives, filament winding and RM application.
DY 9577	Amber or brown semi-solid	-	26-35 ²⁾	-	10 ⁸⁾	High activity above 120°C used for casting, encapsulation, filament winding, pultrusion, molding and electrical tape application

1) with GY 6010, 100°C; 2) Melting point; 3) 120°C; 4) with GT 1999, 180°C; 5) with GT 6063, 180°C; 6) with GT 7013, 150°C; 7) with GY 6010, 35°C; 8) with GY 6010, 130°C

Advanced Materials

Accelerators Additives

Accelerators

Product	Viscosity at 25°C [mPa s]	Amine value [mg KOH/g]	Colour [Gardner]	H+ Equivalent [g/Eq]	Softening point [°C]	Comments/Applications
Accelerator 960-1	120-250	560-675	≤8	-20	-	Tertiary amine accelerator for polyamine, polyamidoamines and anhydrides.
Accelerator 2950	2,000-6,000	640-700	≤10	-75	-	Stable with all Aradur® hardeners. In type 1 EP/PAA same effect as Accelerator 960-1, but double the potlife. Solventfree systems open to foot traffic in less than a day at 5°C.
Accelerator 3130	10-100	-	≤3	-	-	Extreme, unique speeding of drying time (less than half an hour).
DT 3126-2	Fine powder	-	White	-	100-110 ²⁾	Accelerator for hybrid, polyester/TGIC, polyester/Araldite® PT 910 additive and polyester/Araldite® PT 912 additive powder coatings.
XB 5730	-	-	-	-	-	Latent microgel carried imidazole type accelerator with excellent resistance against shear forces.
DY 070	1-5	-	≤3	-	-	Heterocyclic amine. Used with anhydride hardeners to improve reactivity.

Additives

Crosslinker for powder coatings

Product	Supply form	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Melting point (DSC) [°C]	Comments/Applications
PT 710	Pellets (dust free)	8.80-9.80	102-114	84-98	General purpose TGIC crosslinker in granules for the formulation of weatherable polyester powder coatings.
PT 810	Pellets (dust free)	9.3-10.00	100-108	88-98	TGIC crosslinker in low dust supply form suitable for high quality weatherable polyester powder coatings.
PT 910	Granulate	6.50-7.10	141-154	90-102	Multifunctional glycidylester crosslinker for TGIC free weatherable polyester powder coatings.
PT 912	Granulate	6.50-7.10	141-154	82-96	High quality multifunctional glycidylester weatherable epoxy crosslinker with higher functionality than Araldite® PT 910 additive.

Matting agents for powder coatings

Product	Supply form	Softening point [°C]	Flash point [°C]	Comments/Applications
DT 125-2	Fine powder	59-71 ¹⁾	≥200	Solid, wax-free, non-yellowing matting agent for epoxy/polyester hybrid and for polyester/Araldite® PT 810 additive powder coatings. The gloss range covered is >35 for hybrids and >70 for Araldite® PT 810 based systems.
DT 3329-1	Coarse powder	109-117 ²⁾	≥200	Wax containing matting agent for weatherable polyester as well as for epoxy/polyester hybrid powder coatings. The gloss range covered is >25 for hybrids; >40 for polyester/Araldite® PT 810 based systems and >65 for polyester/Araldite® PT 910 or Araldite® PT 912 additive.
DT 3330	Fine powder	127-137 ²⁾	>250	Solid, wax-free matting agent for weatherable, non-yellowing polyester powder coatings cured with Araldite® PT 912 additive in the gloss range 60-80 or for low gloss dry blend systems.
DT 3360	Fine powder	120-135 ²⁾	>250	Solid, wax-free, non-yellowing matting agent for epoxy/polyester hybrid powder coatings in the gloss range 15-40.

Additives for coatings

Product	Supply form	Epoxy index [Eq/kg]	Flash point [°C]	Comments/Applications
DW 1765	Paste	1.20-1.60	>100	Mostly eliminates or greatly reduces exudation / blushing / tackiness and sensitivity to water (water spotting).

1) ISO11357-3; 2) DIN 51920

Advanced Materials

Waterborne system

Waterborne System: Hardeners • Aradur®

Product	Viscosity at 25°C [mPa s]	Amine value [mg KOH/g]	H+ Equivalent [g/Eq]	Colour [Gardner]	Solids [°C]	Comments/Applications
Aradur® 35	19,000-35,000	100-120	~380	≤6	51-55	Polyamine adduct in water with fast low-temperature cure.
Aradur® 36	4,000-7,000	185-225	~165	≤6	79-81	Polyamine adduct in water with good handling and flow. Suitable for waterborne coating and ECC. High solid content.
Aradur® 38	17,000-23,000	170-210	~150	≤6	79-81	Polyamine adduct in water with good handling and flow. Suitable for waterborne coating and ECC.
Aradur® 39	12,000-20,000	120-140	~335	≤5	49-51	Polyamine adduct in water with long pot life, fast cure. (Not recommended with solid resin).
Aradur® 429 Z 75	10,000-20,000	210-240	~190	≤10	74-76	Polyamidoamine adduct in ethanol/sopropanol/Shellsol A (2:2:1).
Aradur® 435	13,000-23,000	160-200	~250	≤10	49-51	Polyamidoamine adduct in water for waterborne coatings and adhesives.
Aradur® 340	18,000-23,000	155-175	~210	≤12	49-51	Polyamidoamine in water with particularly good adhesion and flexibility.
Aradur® 3985	2,000-6,000	170-210	~265	≤6	54-56	Modified polyamine adduct in water. Suitable for flooring and mortar.
Aradur® 3985S	4,000-8,000	200-250	~210	≤6	54-56	Similar to Aradur® 3985 hardener, fast cure. Suitable for flooring and mortar.
Aradur® 3986	15,000-35,000	90-110	~415	≤6	39-41	Modified polyamine adduct in water for the formulation of water-based coatings for application to mineral and metallic substrates. No flash rust inhibitor necessary.
Aradur® 23919	110,000-145,000	-	~355	light yellow	26-30	Polyamidoamine aqueous dispersion for ambient cure with Araldite® GY 23919 resin in 1:1 mix ratio for multipurpose concrete coating applications.

Waterborne System: PU flooring • Arathane®

Product	Epoxy index [Eq/kg]	Epoxy equiv. [g/Eq]	Viscosity at 25°C [mPa s]	Colour [Gardner]	Solids [%]	Comments/Applications
PY 340-2	5.50-5.80	172-182	6,000-8,000	≤3	100	Dispersible in water, non-crystallizing. Used for waterborne coating and ECC.
PZ 323	4.00-4.50	222-250	Slightly thixotropic	white	75-78	Aqueous dispersion of polyfunctional EPN resin with good abrasion resistance, toughness and chemical resistance. Used for coatings, adhesives, fiber-sizing, textiles and paper treatment.
PZ 756/67	~3.55	~282	~ 5000 at 20 °C, thixotropic	white	66-68	Aqueous dispersion of liquid non-crystallizing resin.
PZ 3901	1.77-1.98	505-565	7,000-20,000	white	53.5-56.5	Aqueous dispersion of Type-1 solid resin ² . Used for coatings, adhesives, fiber-sizing, textiles and paper treatment.
PZ 3907-1	0.45-0.57	1,800-2,200	8,000-20,000	white	52-55	Aqueous dispersion of Type-7 solid resin ² . Used for coatings, adhesives, fiber-sizing, textiles and paper treatment.
PZ 3921	1.47-1.64	610-680	250-450	white	49-51	Formulated waterborne epoxy emulsion designed for ambient temperature curing coatings in combination with a carboxyl-functional acrylic latex or waterborne amine Hardeners.
ECN 1400	4.00-4.50	220-250	900-1,500	white	39-41	Aqueous dispersion of polyfunctional ECN resin with improved adhesion, temperature and chemical resistance. Used for coatings, adhesives, fiber-sizing, textiles and paper treatment.
GY 23919	3.08-3.28	305-325	20,000-30,000	white	60-66	Aqueous dispersion for ambient cure with Aradur 23919 hardener in 1:1 mix ratio for multipurpose concrete coating applications.

1) 23°C; 2) in water and 2-propoxyethanol

We see a better world

We focus on developing products and solutions to solve new challenges, such as global demand for alternative energy. We enable our customers to be active in green technologies and introduce new eco-friendly processes as well as alternative materials to help reduce carbon footprint and preserve resources. By leveraging our core competencies, which include synthesis and formulation, testing and analysis, process manufacturing technology and technical service, we can develop sustainable products that benefit our customers, consumers and planet as a whole.

Huntsman Advanced Materials

We are a leading global supplier of synthetic and formulated polymer systems for customers requiring high-performance materials which outperform the properties, functionality and durability of traditional materials. Over 2,200 associates at 13 locations worldwide, work to fulfill this promise day by day.

More than 3,000 companies around the world use Huntsman Advanced Materials technologies in key markets such as adhesives and inks, aerospace, automotive, coatings, construction, electronics, medical, marine, power transmission and distribution, sports equipment and wind power generation.

For more information

EUROPE / AFRICA Huntsman Advanced Materials (Switzerland) GmbH • Klybeckstrasse 200 P.O. Box 4002 Basel • Switzerland • Tel +41 61 299 11 11 • Fax +41 61 299 11 12

INDIA / MIDDLE EAST Huntsman Advanced Materials (India) Pvt. Ltd • 5th Floor, Bldg. No. 10 Solitaire Corporate Park • 167, Guru Hargovindji Marg, Chakal Andheri (East) • Mumbai - 400 093 India • Tel +91 22 4095 1556 - 60 • Fax+91 22 4095 1300/1400/1500

AMERICAS Huntsman Advanced Materials Americas Inc. • 10003 Woodloch Forest Drive The Woodlands • Texas 77380, USA • Tel +1 888 564 9318 • Fax +1 281 719 4047

ASIA / PACIFIC Huntsman Advanced Materials (Guangdong) Co., Ltd • Rooms 4903-4906, Maxdo Centre, 8 Xing Yi Road, Shanghai 200336, China • Tel +86 21 2208 7588 • Fax +86 21 2208 7511

www.huntsman.com/advanced_materials
advanced_materials@huntsman.com



Legal information

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof.

Except where explicitly agreed in writing otherwise, the sale of product described herein ("Product") is subject to the terms and conditions of sale of the Huntsman company from which you purchased the product (or those of the authorised distributor, as the case may be).

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA; Huntsman Advanced Materials (Europe) BVBA in Europe; and Huntsman Advanced Materials (Australia) Pty Ltd, Huntsman Advanced Materials (Hong Kong) Ltd, Huntsman Advanced Materials (Guangdong) Company Limited, Huntsman Advanced Materials (India) Pvt Ltd, Huntsman Japan KK, Huntsman Advanced Materials (Singapore) Pte Ltd and Huntsman Advanced Materials (Taiwan) Corporation in Asia Pacific.

The following supersedes Buyer's documents.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN IS TO BE CONSTRUED AS A REPRESENTATION, WARRANTY OR CONDITION OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES. No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Data and results are based on controlled conditions and/or lab work. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. Buyer should (i) obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, (ii) take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product and (iii) comply with and ensure that its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product comply with all safety information contained in the applicable Material Safety Data Sheets, Technical Data Sheets or other instructions provided by Huntsman and all applicable laws, regulations and standards relating to the handling, use, storage, distribution and disposal of and exposure to the Product.

Please note that products may differ from country to country. If you have any queries, kindly contact your local Huntsman representative.

Araldite®, Tactix®, Quatrex®, Arathane®, Rhodэфtal®, Aradur® are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2012 Huntsman Corporation or an affiliate thereof. All rights reserved.
Ref No. AdMat_SC_02/12_EN_AP