

# Product Selector Guide

# HUNTSMAN

Enriching lives through innovation

## Two Component Epoxy Systems for the Production of Moulds and Tools

Resin	Hardener	Mix ratio (pbw)	Colour	Density g/cm <sup>3</sup>	Pot life (min.)*	Castable layer thickness (mm)	Applications	Temperature resistance after respective cure cycle (ISO 75) °C					
								50	100	150	200	250	
<b>RenGel® Gelcoats</b>													
SW 10	HY 2404	100 : 10	white	1.5	20	-	Working moulds (ceramic), negatives, models, jigs	60-80	easily machinable, polishable, low odour				
	HY 5159	100 : 8		1.5	60								
SW 404	HY 2404	100 : 10	blue	1.8	15	-	Foundry patterns, copy-milling models, foaming moulds	80-100	abrasion resistant				
	HY 5159	100 : 8		1.8	50								
SW 18	HY 2404	100 : 20	green	1.3	10-15	-	Wet lay-up tools, vacuum forming tools	85-100	polishable, styrene resistant				
	HY 5159	100 : 16		1.3	25								
SW 419-1	HV 2419	100 : 13	black	2.3	15-20	-	Metaforming tools, foundry patterns, general model making	60-70	abrasion resistant				
SW 56	HY 2404	100 : 13	caramel	1.5	10-15	-	Pressure casting moulds (ceramic), wet lay-up tools	100-120	workable, polishable, chemical resistant				
	HY 5159	100 : 10		1.5	25-30								
SW 5200	HY 5211	100 : 20	black	1.6	18 hrs	-	Pre-preg tools, high temperature tooling applications		high temperature	180-200			
	HY 5212	100 : 20	black	1.5	10 hrs								
	HY 5213	100 : 16	black	1.6	270								
<b>RenGel® Coupling Coat</b>													
P 99	HY 5159	100 : 11	grey	1.5	30	-	Coupling coat between gelcoat and backing	120	multipurpose coupling coat				
<b>RenCast® Casting Systems</b>													
CW 20	HY 49	100 : 5	blue	2	110	30	Foundry patterns, copy-milling models, metaforming tools, foam moulds	65-70	mineral filled, abrasion resistant				
CW 2418-1	HY 5160	100 : 15	black	2.3	120	80	Metaforming tools, casting of dowel bushes, general model making, full & face casting, foundry patterns	50-65	metal filled, cure: slow/medium/fast				
	HY 5161	100 : 15		2.3	60	20							
	HY 5162	100 : 15		2.3	30	10							
	HY 5118	100 : 20		2.2	80	40							
CW 2215	HY 5160	100 : 20	yellow	1.6	120	80	Suitable for a wide range of applications	50-65	easily machinable, colourable, cure: slow/medium/fast				
	HY 5161	100 : 20		1.6	45	20							
	HY 5162	100 : 20		1.6	25	10							
CW 5156-1	HY 5158	100 : 8	grey	1.6	80	80	Foam moulds vacuum forming moulds	130	chemical resistant, easily machinable				
CW 47	HY 33	100 : 15	grey	1.85	4.5 hrs	100	Pre-preg tools, vacuum forming moulds, injection moulds, high temperature tooling applications		castable up to 100mm, easily machinable	200-210			
<b>RenLam® Laminating Systems</b>													
CY 219	HY 5160	100 : 50	pale yellow	1.1	80	-	Laminates and backfilling with a variety of fillers	45-60	transparent, tack-free with adjustable reactivity				
	HY 5161	100 : 50	pale yellow	1.1	40								
	HY 5162	100 : 50	pale yellow	1.1	20								
M-1	HY 956	100 : 20	pale yellow	1.1	30	-	Laminates and backfilling with a variety of fillers	50	transparent, room temperature curing, good impregnation				
LY 113	HY 97-1	100 : 32	pale yellow	1.1	80	-	Structural and special applications	120	low viscosity, good room temperature curing				
LY 5210	HY 5211	100 : 40	amber	1.1	24 hrs	-	Pre-preg lay up tools, parts and structures, high temperature tooling applications		high temp, partial curing at room temperature, long pot life	180-210			
	HY 5212	100 : 40	amber	1.1	12 hrs								
	HY 5213	100 : 32	amber	1.1	180								
<b>RenLam® Laminating Pastes</b>													
LY 573-2	HY 2959	100 : 15	fibrous paste grey	1.1	45-60	20	Glass-fibre reinforced backing structures	50	up to 20 mm layer thickness, hand applied				
LV 10	HY 97 blue	100 : 20	grey blue	0.75	60	10	Light, stiff laminated shells and backing structures	125	light paste, hand applied				
<b>RenPaste® Modeling Pastes</b>													
SV 427-2	HV 427-1	100 : 100	brown	0.6	40	20	Models and patterns, general alteration or repair of models + patterns	50-55	room temperature curing, with other hardeners suitable for bonding RenShape® boards				
SV 36	HV 36	100 : 100	brown	0.5	60	40	Light models, patterns and repairs	50-55	no pin holes, light, easily machinable, hand applied, layer thickness 40 mm				


\* gelcoats: 250 ml, laminating resins: 500 ml, casting systems and pastes: 1l

[www.huntsman.com/advanced\\_materials](http://www.huntsman.com/advanced_materials)  
[advanced\\_materials@huntsman.com](mailto:advanced_materials@huntsman.com)

Huntsman Advanced Materials (Switzerland) GmbH  
 Klybeckstrasse 200, CH 4057 BASEL Tel: +41 61 966 33 33 Fax: +41 61 966 35 19

While all the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NOTHING HEREIN IS TO BE CONSTRUED AS A WARRANTY, EXPRESS OR OTHERWISE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO DETERMINE THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. The sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials (Europe) BVBA or of its affiliated companies.

©RenShape Solutions, RenCast, RenGel, RenLam and RenPaste are registered trademarks of Huntsman corporation or an affiliate thereof in one or more, but not all countries. Copyright © 2006 Huntsman Advanced Materials (Switzerland) GmbH.



RenShape  
solutions