

Enriching lives through innovation

# **Essential Building Blocks** for Coatings, Adhesives & Sealants and Composites Applications



Huntsman Corporation is a leading global producer of intermediate chemistries and technologies that add value to customers worldwide. Our customers benefit from world-scale manufacturing capacity backed with highly skilled regional customer support, in-depth technical expertise and dedicated market knowledge. The Huntsman Performance Products product lines include ethylene amines, cycloaliphatic amines, morpholine derivatives, polyetheramines, specialty amines like alkylalkanol amines and substituted propylamines, as well as various carbonates.

# **Product Families**

# **AMINES**

# **JEFFAMINE®** Polyetheramines

JEFFAMINE<sup>®</sup> polyetheramines typically impart increased flexibility and toughness, and are low viscosity and low color products. Historically, the core JEFFAMINE<sup>®</sup> polyetheramine family consisted of monoamines, diamines and triamines based on the core polyether backbone structure. More recently, the addition of hindered, high-conversion, polytetramethylene glycol (PTMEG)-based, and secondary polyetheramines has increased the utility of these products.

# Ethyleneamines

Huntsman offers a complete line of ethylene amines. We manufacture our ethyleneamines via the ethylene dichloride/ammonia process. Ethyleneamines are widely used as hardeners in epoxy systems that are cured under ambient conditions, and are used to produce thermoplastic polyamide resins for hot-melt adhesives.

## **Cycloaliphatic Amine**

JEFFAMINE<sup>®</sup> RFD-270 amine is a polyetheramine with a cycloaliphatic segment combining the advantages of both product families. Color stable, low blush tendency, low viscosity and good flexibility combined with enhanced glass transition temperature, hardness and modulus.

## **Morpholine and Derivatives**

Morpholine and derivatives may be used as an accelerator/catalyst in epoxy formulations or as catalyst/initiator in UV curable acrylic-based systems for coatings and adhesives.

## **Specialty Amines**

Alkylalkanol amines such as N-methyldiethanolamine (MDEA), and substituted propylamines such as aminopropylmorpholine (APM), dimethylaminopropylamine (DMAPA) are typically used as epoxy accelerators or curing agents, and as intermediates for coatings.

# CARBONATES

#### **JEFFSOL®** Carbonates

Huntsman's carbonates provide a more environmentally friendly alternative to products such as methylene chloride, acetone and aromatic solvents. Our carbonates are typically used as cure accelerator in silicate (water-glass) binding and in phenol formaldehyde resins. As solvent and (reactive) diluent in epoxy formulations and urethane systems, in industrial cleaners and paint removers, and in polyester synthesis.

	TYPICAL PROPERTIES									FUNCTION						
AMINES	Approximate Molecular Weight, g/mol	Typical Total Amine Content, meq/g	Amine Hydrogen Equivalent Weight (AHEW), g/eq	Density, g/ml @ 25°C	Viscosity, cSt @ 25°C	Flash Point, PMCC, °C	Coatings	Adhesives & Sealants	Composites	EP - Epoxy Curing Agent	PM - Polymer & Resin Modifier	IM - Intermediate	S - Solvent / RD - Reactive Diluent	AC - Accelerator / Catalyst	pH - pH Control	
POLYETHERAMINES																
JEFFAMINE <sup>®</sup> D-series		1														
<b>JEFFAMINE<sup>®</sup> D-230 amine</b> Polyoxypropylene diamine	230	8.1-8.7	60	0.948	9.5	121	•		•	EP	PM		RD			
<b>JEFFAMINE® D-400 amine</b> Polyoxypropylene diamine	430	4.1-4.7	115	0.972	22	163	•		•	EP	PM		RD			
<b>JEFFAMINE® D-2000 amine</b> Polyoxypropylene diamine	2000	0.98-1.05	514	0.991	250	185				EP	PM					
JEFFAMINE® D-4000 amine Polyoxypropylene diamine	4000	0.44-0.52	1000	0.994	877	227	•			EP	PM					
<b>JEFFAMINE® D-205 amine</b> Slow reactivity aliphatic polyether diamine	219	8.6 min.	58	0.943	7	121			•	EP						
JEFFAMINE <sup>®</sup> T-series								1								
<b>JEFFAMINE® T-403 amine</b> Polyoxypropylene triamine	440	6.1-6.6	81	0.978	75	196	•		•	EP	PM		RD			
<b>JEFFAMINE® T-3000 amine</b> Polyoxypropylene triamine	3000	0.90-0.98	530	0.996	370	235	•		•	EP	PM					
<b>JEFFAMINE® T-5000 amine</b> Polyoxypropylene triamine	5000	0.50-0.54	952	0.997	820	213	•		•	EP	PM					
JEFFAMINE <sup>®</sup> EDR-series																
JEFFAMINE® EDR-148 amine Higher reactivity polyether diamine	148	12.7 min.	37	0.998	8	129	•		•	EP	PM	IM	RD			
JEFFAMINE® THF-series																
<b>JEFFAMINE® THF-100 amine</b> PTMEG/PPG copolymer based diamine	1000	1.87-2.06	260	0.976	120 @ 40°C	238	•			EP	PM					
JEFFAMINE® M-series								I								
JEFFAMINE <sup>®</sup> M-600 amine PEG/PPG copolymer based monoamine	600	1.58-1.79	291	0.979	30	129	•				PM				pН	
JEFFAMINE <sup>®</sup> M-1000 amine PEG/PPG copolymer based monoamine	1000	0.94 min.	489	1.07 @ 38°C	Waxy solid	98	•				PM				pН	
JEFFAMINE® M-2005 amine PEG/PPG copolymer based monoamine	2000	0.42-0.50	1045	1.00	130 @ 38°C	235					PM				pН	
JEFFAMINE® M-2070 amine PEG/PPG copolymer based monoamine	2000	0.45 min.	1040	1.07	185 @ 38°C	243	•				PM				pН	
<b>JEFFAMINE® M-3085 amine</b> PEG/PPG copolymer based monoamine	3000	0.35 min.	1520	1.00	Solid	>135C					PM	IM			pН	
JEFFAMINE® ED-series		1														
JEFFAMINE <sup>®</sup> ED-600 amine PEG/PPG copolymer based diamine	600	3.00-3.43	132	1.04	70 @ 20°C	160	•				PM					
<b>JEFFAMINE® ED-900 amine</b> PEG/PPG copolymer based diamine	900	1.80-2.25	250	1.06 @ 38°C	120	174					PM					
<b>JEFFAMINE® ED-2003 amine</b> PEG/PPG copolymer based diamine	2000	0.90-1.05	575	1.07 @ 50°C	135 @ 50°C	260	•				PM					

			ТҮР	ICAL PROPERTIE	S		APP	LICAT	TION	FUNCTION						
AMINES	Approximate Molecular Weight, g/mol	Typical Total Amine Content, meq/g	Amine Hydrogen Equivalent Weight (AHEW), g/eq	Density, g/ml @ 25°C	Viscostiy, cSt @ 25°C	Flash Point, PMCC, °C	Coatings	Adhesives & Sealants	Composites	EP - Epoxy Curing Agent	PM - Polymer & Resin Modifier	IM - Intermediate	S - Solvent / RD - Reactive Diluent	AC - Accelerator / Catalyst	pH - pH Control	
ETHYLENEAMINES																
<b>EDA</b> Ethylenediamine	60	33	~15	0.90 @ 20°C	2 cP @ 20°C	43				EP	PM	IM				
<b>DETA</b> Diethylenetriamine	103	29	~21	0.95 @ 20°C	7 cP @ 20°C	102				EP	PM	IM				
<b>TETA</b> Triethylenetetramine	151	26	~24	0.98 @ 20°C	14 cP @ 20°C	118				EP	PM	IM				
<b>TEPA</b> Tetraethylenepentamine	200	24	~27	0.99 @ 20°C	23 cP @ 20°C	>177				EP	PM	IM				
ECA-29 Polyamine mixture	271	22	~36-38	1.01 @ 20°C	225 cP @ 25°C	>182				EP	PM	IM				
<b>AEP</b> Aminoethylpiperazine	129	23	43	0.99 @ 20°C	10 cP @ 20°C	100				EP	PM	IM		AC		

# CYCLOALIPHATIC AMINE

JEFFAMINE® RFD-270 amine Includes a polyetheramine segment 270 7.3-8.0 67.0	0.96	68	>149				EP					
--	------	----	------	--	--	--	----	--	--	--	--	--

# MORPHOLINE

MOR Morpholine	87	na	na	1.00	2 cP @ 20°C	35			PM	IM	AC	
NMM N-methylmorpholine	101	na	na	0.92	1	13					AC	
<b>NEM</b> N-ethylmorpholine	115	na	na	0.91	1	30					AC	

# SPECIALTY AMINES

Accelerator									 		 	
Accelerator 400 Epoxy curing promoter	na	na	145	1.089	810	90	•	•			AC	
Alkylalkanol Amines												
<b>DMEA</b> Dimethylethanolamine	89	na	na	0.890	3 @ 20°C	41	•		PM		AC	рH
MDEA N-methyldiethanolamine	119	na	na	1.04	37 @ 38°C	140			PM		AC	pН
MMEA Monomethylethanolamine	75	na	na	0.900	14 @ 20°C	71			PM		AC	pН
JEFFADD <sup>®</sup> series												
JEFFADD <sup>®</sup> HEEU additive N-(2-Hydroxyethyl)ethylene urea	116	na	na	Solid	84 @ 60°C	>221			PM	IM		

			TYPIC	AL PROPERT	TION			FUNCTION							
AMINES	Approximate Molecular Weight, g/mol	Typical Total Amine Content, meq/g	Amine Hydrogen Equivalent Weight (AHEW), g/eq	Density, g/ml @ 25°C	Viscosity, cSt @ 25°C	Flash Point, PMCC, °C	Coatings	Adhesives & Sealants	Composites	EP - Epoxy Curing Agent	PM - Polymer & Resin Modifier	IM - Intermediate	S - Solvent / RD - Reactive Diluent	AC - Accelerator / Catalyst	pH - pH Control
SUBSTITUTED PROPYLAMIN	ES				1										
APM Aminopropylmorpholine	144	na	na	0.990	6 @ 20°C	100						IM	RD	AC	pН
<b>DMAPA</b> Dimethylaminopropylamine	102	na	51	0.820	1 @ 20°C	29		•				IM	RD	AC	
DMDPTA N, N-dimethyldipropylenetriamine	159	na	53	0.870	10-20	>100				EP	PM				
APMMEA N-aminopropylmonomethylethanolamine	132	15	na	0.969	47	128					PM			AC	pН
<b>APMMEA-WB</b> N-aminopropylmonomethylethanolamine*	na	12	na	1.01	74	>100								AC	pН
APDEA N-aminopropyldiethanolamine	162	12	na	1.10	245 @ 38°C	196					PM	IM		AC	
MOPA Methoxypropylamine	89	na	na	0.870	0.8 @ 38°C	27						IM		AC	pН

\* In water

		ТҮРІ	CAL PROPE	V	APPLICATION			FUNCTION							
CARBONATES	Approximate Molecular Weight, g/mol	Density, g/ml @ 25°C	Viscosity, cSt @ 25°C	Flash Point, PMCC, °C	Boiling point, 760mm Hg, °C	Vapor pressure, kPa @ 20°C	EU Directive 1999 / 13 / EC based on vapour pressure	EU Directive 2004 / 42 / EC based on boiling point	Coatings	Adhesives & Sealants	Composites	PM - Polymer & Resin Modifier	IM - Intermediate	S - Solvent / RD - Reactive Diluent	C - Cleaner Solvent
CARBONATES															
JEFFSOL <sup>®</sup> EC carbonate Ethylene carbonate	88	1.32 @ 40°C	2 @ 40°C	160	248	<0.01	Zero VOC		-			PM	IM	S / RD	
JEFFSOL <sup>®</sup> PC carbonate Propylene carbonate	102	1.20	2.5	135	242	<0.01	Zero VOC					PM	IM	S / RD	С
JEFFSOL <sup>®</sup> GC carbonate Glycerine carbonate	118	1.38	85	>190	>250	<0.01	Zero VOC	Zero VOC				PM	IM	S / RD	
JEFFSOL <sup>®</sup> MCH methylcyclohexane Environmentally friendly aliphatic solvent	98	0.77	1	-4	101	4.8								S	С

# About Huntsman

Huntsman Corporation is a publicly traded global manufacturer and marketer of differentiated and specialty chemicals with 2022 revenues of approximately \$8 billion from our continuing operations. Our chemical products number in the thousands and are sold worldwide to manufacturers serving a broad and diverse range of consumer and industrial end markets. We operate more than 60 manufacturing, R&D and operations facilities in approximately 30 countries and employ approximately 7,000 associates within our continuing operations. For more information about Huntsman, please visit the company's website at www.huntsman.com.

# Huntsman Performance Products

Performance Products brings together innovation and world-leading process technologies to produce components used to formulate products that enhance people's lives. Our leading global positions in the manufacture and sale of amines, maleic anhydride and carbonates enable us to serve diverse consumer and industrial end markets, including energy, automotive and transportation, coatings and adhesives, construction and infrastructure, electronics, and industrial manufacturing. With 10 manufacturing facilities in North America, Europe, the Middle East and Asia, we produce and sell over 350 products to over 900 global customers, and provide extensive pre- and post-sales technical service support. The division had 2022 revenues of USD 1.7 billion.



# www.huntsman.com/pp

# HUNTSMAN

# Enriching lives through innovation

#### **Global Headquarters**

#### Americas

Huntsman Corporation 10003 Woodloch Forest Drive The Woodlands, Texas, 77380 USA Tel : +1-281-719-6000

#### **Asia Pacific**

Huntsman Performance Products No. 455 Wenjing Road Minhang Economic & Technological Development Zone Shanghai 200245 P. R. China Tel : +86-21-3357-6588

#### Europe, Middle East & Africa

Huntsman Performance Products Bürohaus an der Alten Oper Neue Mainzer Strasse 75 60311 Frankfurt Germany

#### For more information, please contact your local Huntsman representative or drop us an email at pp\_enquiry@huntsman.com

#### Disclaimer

Huntsman Performance Products warrants only that its products meet the specifications agreed with the buyer. Typical properties, where stated, are to be considered as representative of current production and should not be treated as specifications. While all the information and be reated as specificatoris. Write all the information and recommendations in this publication are to the best of our knowledge, information and belief accurate at the date of publication, NO GUARANTY, WARRANTY OR REPRESENTATIONS IS MADE, INTENDED OR IMPLIED AS TO THE CORRECTNESS OR SUFFICIENCY OF ANY INFORMATION OR RECOMMENDATIONS OR AS TO THE WEEDCHARTABILITY OR ETHESS OF ANY MERCHANTABILITY, SUITABILITY OR FITNESS OF ANY PRODUCTS FOR ANY PARTICULAR USE OR PURPOSE. IN ALL CASES, IT IS THE RESPONSIBILITY OF THE USER TO ALL DRACE, IT IS THE REPORTING TO THE OWNER OWNER THE APPLICABILITY OF SUCH INFORMATION AND RECOMMENDATIONS AND THE SUITABILITY OF ANY PRODUCT FOR ITS OWN PARTICULAR PURPOSE. NOTHING IN THIS PUBLICATION IS TO BE CONSTRUED. AS RECOMMENDING THE INFRINGEMENT OF ANY PATENT OR OTHER INFRINGEMENT OF ANY PATENT OR OTHER INTELLECTUAL PROPERTY RIGHT AND NO LIABILITY ARISING FROM ANY SUCH INFRINGEMENT IS ASSUMED. NOTHING IN THIS PUBLICATION IS TO BE VIEWED AS A LICENSE UNDER ANY INTELLECTUAL PROPERTY RIGHT. Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Performance Products containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards. Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on the manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users. Huntsman Performance Products is an international division of Huntsman International LLC. Huntsman Performance Products trades through Huntsman affiliated companies in different countries such as Huntsman Petrochemical LLC in the USA and Huntsman Holland BV in Western Europe. Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the Huntsman Terms and Conditions of Sale, which can be found at <u>https://www.huntsman.com/sales-</u> which are incorporated herein by reference. s-terms-conditions.

JEFFADD<sup>®</sup>, JEFFAMINE<sup>®</sup> and JEFFSOL<sup>®</sup> are registered trademarks of Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

 $\ensuremath{\textcircled{}}$  2024. Huntsman Corporation or an affiliate thereof. All rights reserved.