

Advanced Materials

HYPRO® 1300X16 ATBN[#]

Reactive Toughener and flexibilizer

DATA SHEET

Amine Terminated copoly(Butadiene-Acrylonitrile)

Product Description

Hypro Reactive Liquid Polymers (RLP) are 100% solids liquid rubbers used to improve the toughness, flexibility, adhesion and impact resistance of thermoset resin systems including epoxies, vinyl esters, unsaturated polyesters, acrylics and urethanes.

HYPRO® 1300X16 ATBN is an amine-terminated butadiene-acrylonitrile copolymer used predominantly with other amine-functional compounds to improve product performance when added to thermoset resin systems. The amine structure in HYPRO® 1300X16 is based on N-aminoethylpiperazine (N-AEP).

Applications

- Structural adhesive paste
- Composites
- Coatings and linings for corrosion resistance
- Construction joint sealers and mastics
- End uses include aerospace, construction, composites and industrial applications

Benefits

- Enhances the toughness and flexibility of thermoset resins
- Improves adhesion to substrates that are difficult to bond to
- Mid-range acrylonitrile-containing ATBN (18%) which improves compatibility with epoxy system
- Increases low-temperature mechanical properties
- Increases impact and wear resistance

Key data

Specified key data

Viscosity at 25 °C (Brookfield)	150 000 – 250 000	[mPa s]
Amine Equivalent weight (titration)	800 - 1000	[g/Eq]

Specified key data are individually checked throughout and guaranteed.

Typical key data

Appearance	Liquid polymer, amber in color
Gardner colour	3 - 8

Data which is described in this document as 'typical' is not analyzed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

[#] In addition to the brand name product denomination may show different appendices, which allows us to differentiate between our production sites: e.g. BD = Germany, US = United States, IN = India, CI = China, etc. These appendices are in use on packaging, transport and invoicing documents. Generally, the same specifications apply for all versions. Please address any additional need for clarification to the appropriate Huntsman contact.

HYPRO® ATBN Standard Line of Products —Typical Properties

HYPRO® Polymers	2000X173 ATB	1300X21 ATBN	1300X16 ATBN	1300X45 ATBN	1300X35 ATBN	1300X42 ATBN
Acrylonitrile Content, %	0	10	18	18	26	18
Amine Equivalent Weight (AEW), g/eq*	950	1,200	900	1,850	700	450
Amine Value	59	47	62	30	80	125
Brookfield Viscosity, mPa.s or cP @ 27 °C (81°F)	180,000	160,000	200,000	375,000	500,000	100,000
Specific Gravity @ 25/25 (77 °F)	—	0.938	0.956	—	0.978	0.942
Glass Transition Temp., °C**	—	-65	-51	—	-38	-594
Free Amine Level, %	4	2	5	< 0.1	7	10

*For secondary amine-terminated polymers, AEW value may be used as Amine Hydrogen Equivalent Weight, whereas for HYPRO 1300X42 ATBN, a primary amine-terminated material, Weight per Active Hydrogen is AEW/2.

**Measured via DSC (differential scanning calorimeter).

Typical Epoxy Formulation Using HYPRO® 1300X16 ATBN

Formulation	1	2
ARALDITE® GY 250	100	100
ARADUR® 140	60	56.4
Calcium Carbonate	30	30
HYPRO® 1300X16 ATBN	—	30

Cured Properties

Substrate: sandblasted steel		
Cure: 2 weeks at room temperature	1	2
Lap shear strength, psi (MPa)		
@ -40 °C	1,370 (9.45)	2,260 (15.58)
@ R.T.	1,600 (11.03)	2,500 (17.24)
T-peel strength, pli (N/mm)		
@ R.T.	3.3 (0.579)	35.0 (6.14)

Cure: 2 hours @ 60 °C plus 1 hour @ 100°C		
Lap shear strength, psi, (MPa)	1	2
@ -40 °C	2,148 (14.81)	3,128 (21.57)
@ R.T.	2,550 (17.58)	2,612 (18.01)
T-peel strength, pli (N/mm)		
@ R.T.	4.2 (0.736)	40.0 (7.02)

Storage	<p>HYPRO® 1300X16 ATBN should be stored in a dry place, preferably in the sealed original container, at temperatures between 2 and 40 °C. The product should not be stored exposed to direct sunlight.</p> <p>Keep away from food, drink and animal feeding stuff.</p>
Handling precautions	<p>HYPRO® 1300X16 ATBN is amine functional material, irritation can result from repeated or prolonged contact. The symptoms of this irritation may appear as a mild reddening or a more pronounced rash. It is, therefore, important to avoid skin contact where possible. Butyl rubber gloves, full eye protection and protective clothing are recommended.</p> <p>Skin contact: Wash well with soap and water. Remove contaminated clothing and wash thoroughly before reusing. It is recommended that resin not be removed from skin with solvents since solvents increase contact and encourage penetration. Moreover, solvents of themselves dry and crack the skin.</p> <p>Eye contact: Flush immediately with large quantities of water. Contact a physician.</p> <p>Refer to the Safety Data Sheet on HYPRO® 1300X16 ATBN for additional safety and health information. The SDS is revised as new data becomes available.</p>

Huntsman Advanced Materials

(Switzerland) GmbH
Klybeckstrasse 200
4057 Basel
Switzerland

Tel: +41 (0)61 299 11 11
Fax: +41 (0)61 299 11 12

www.huntsman.com/advanced_materials
Email: advanced_materials@huntsman.com



Huntsman Advanced Materials warrants only that its products meet the specifications agreed with the user. Specified data are analysed on a regular basis. Data which is described in this document as 'typical' or 'guideline' is not analysed on a regular basis and is given for information purposes only. Data values are not guaranteed or warranted unless if specifically mentioned.

The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication. While all the information and recommendations in this publication are, to the best of Huntsman Advanced Material's knowledge, information and belief, accurate at the date of publication, nothing herein is to be construed as a warranty, whether express or implied, including but without limitation, as to merchantability or fitness for a particular purpose. In all cases, it is the responsibility of the user to determine the applicability of such information and recommendations and the suitability of any product for its own particular purpose.

The behaviour of the products referred to in this publication in manufacturing processes and their suitability in any given end-use environment are dependent upon various conditions such as chemical compatibility, temperature, and other variables, which are not known to Huntsman Advanced Materials. It is the responsibility of the user to evaluate the manufacturing circumstances and the final product under actual end-use requirements and to adequately advise and warn purchasers and users thereof.

Products may be toxic and require special precautions in handling. The user should obtain Safety Data Sheets from Huntsman Advanced Materials containing detailed information on toxicity, together with proper shipping, handling and storage procedures, and should comply with all applicable safety and environmental standards.

Hazards, toxicity and behaviour of the products may differ when used with other materials and are dependent on manufacturing circumstances or other processes. Such hazards, toxicity and behaviour should be determined by the user and made known to handlers, processors and end users.

Except where explicitly agreed otherwise, the sale of products referred to in this publication is subject to the general terms and conditions of sale of Huntsman Advanced Materials LLC or of its affiliated companies including without limitation, Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas Inc., Huntsman Advanced Materials (UAE) FZE, Huntsman Advanced Materials (Guangdong) Company Limited, and Huntsman Advanced Materials (Hong Kong) Ltd.

Huntsman Advanced Materials is an international business unit of Huntsman Corporation. Huntsman Advanced Materials trades through Huntsman affiliated companies in different countries including but not limited to Huntsman Advanced Materials LLC in the USA and Huntsman Advanced Materials (Europe) BVBA in Europe.

All trademarks mentioned are either property of or licensed to Huntsman Corporation or an affiliate thereof in one or more, but not all, countries.

Copyright © 2020 Huntsman Corporation or an affiliate thereof. All rights reserved.