

# **HYPRO® 1300X16 ATBN Amine-Terminated Butadiene-Acrylonitrile**

## **Product Description**

HYPRO® reactive liquid polymers (RLPs) are 100% liquid rubbers used to improve the toughness, flexibility, adhesion and impact resistance of thermoset resin systems including epoxies, vinyl esters, unsaturated polyesters, acrylics and urethanes. HYPRO® 1300X16 ATBN polymer is an amine-terminated butadiene-acrylonitrile copolymer used predominantly with other amine-functional compounds to improve product performance when added to thermoset resin systems. The amine structure in HYPRO® 1300X16 ATBN polymer is based on N-aminoethylpiperazine (N-AEP).

## **Applications**

- Structural adhesive paste
- Composites
- Coatings and linings for corrosion resistance
- Construction joint sealers and mastics
- End uses include aerospace, construction, composites and industrial applications

## **Benefits & Features**

- Enhances the toughness and flexibility of thermoset resins
- Improves adhesion to substrates that are difficult to bond to
- Mid-range acrylonitrile-containing ATBN (18%) improves epoxy compatibility
- Increases low-temperature mechanical properties
- Increases impact and wear resistance

## **Typical Properties**

Property	HYPRO® 1300X16 ATBN
Appearance	Viscous liquid, amber (3-8 Gardner Color)
Actives Level, %	100
Brookfield Viscosity, cP at 27°C (81 °F)	150,000 – 250,000
Amine Equivalent Weight, g/eq	800 – 1000

### HYPRO ATBN Standard Line of Products —Typical Properties

HYPRO® Polymers	2000X173 ATB	1300X21 ATBN	1300X16 ATBN	1300X45 ATBN	1300X35 ATBN	1300X42 ATBN
Acrylonitrile Content, %	0	10	18	18	26	18
Amine Equivalent Weight (AEW), g/eq*	950	1,200	900	1,850	700	450
Amine Value	59	47	62	30	80	125
Brookfield Viscosity, cP at 27°C (81°F)	180,000	160,000	200,000	375,000	500,000	100,000
Specific Gravity at 25°C (77 °F)	—	0.938	0.956	—	0.978	0.942
Glass Transition Temp., °C (°F) **	—	-65 (-85)	-51 (-60)	—	-38 (-36)	-59 (-74)
Free Amine Level, %	4	2	5	< 0.1	7	10

\*For secondary amine-terminated polymers, AEW value may be used as Amine Hydrogen Equivalent Weight, whereas for HYPRO® 1300X42 ATBN polymer, a primary amine-terminated material, Weight per Active Hydrogen is AEW/2.

\*\*Measured via DSC (differential scanning calorimeter).

### Typical Epoxy Formulation Using HYPRO® 1300X16 ATBN Polymer

Formulation			1	2
DGEBA Liquid Epoxy (EEW-190)			100	100
Polyamidoamine			60	56.4
Calcium Carbonate			30	30
HYPRO® 1300X16 ATBN			—	30
Cured Properties				
Cure Schedule		Test Temp	Result	Result
Lap shear strength, psi (MPa)	2 weeks at 25 °C	at-40 °C	1,370 (9.45)	2,260 (15.58)
		at 25 °C	1,600 (11.03)	2,500 (17.24)
	2 hours at 60 °C + 1 hour at 100 °C	at-40 °C	2,148 (14.81)	3,128 (21.57)
		at 25 °C	2,550 (17.58)	2,550 (17.58)
T-peel strength, pli (N/mm)	2 weeks at 25 °C	at 25 °C	3.3 (0.579)	35.0 (6.14)
	2 hours at 60 °C + 1 hour at 100 °C	at 25 °C	4.2 (0.736)	4.2 (0.736)

Substrate: sandblasted cold rolled steel

### Storage

**HYPRO® 1300X16 ATBN** material should be stored in a dry place, in the sealed original containers, at temperatures between **+2°C and +40°C (+35.6°F and +104°F)**. Under these storage conditions, the product has a shelf life of **6 months** (from date of manufacture). The products should not be exposed to direct sunlight.

### Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest SDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

### First Aid!

Refer to SDS as mentioned above.

**KEEP OUT OF REACH OF CHILDREN**

**FOR PROFESSIONAL AND INDUSTRIAL USE ONLY**

### Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas LLC, or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman, if any.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

**HYPRO®** is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

**Copyright © 2020 Huntsman International LLC.**

### Customer Support Center:

**Huntsman Corporation**  
10003 Woodloch Forest Dr  
The Woodlands, TX 77380  
Tel: +1 (888) 564-9318  
Fax: +1 (281) 719-6416  
[www.huntsman.com](http://www.huntsman.com)