

VERSAMID[®] 125 Polyamide Curing Agent

Product Description

VERSAMID[®] 125 curing agent is a medium viscosity, reactive polyamide based on dimerized fatty acid and polyamines designed for use with solid or liquid epoxy resins for tough, chemical-resistant thermoset coating applications that cure at room temperature. This resin is also useful in adhesive applications. VERSAMID[®] 125 curing agent and epoxy resin systems are generally harder than, and cure more rapidly than, VERSAMID[®] 140 systems. It is often blended with VERSAMID[®] G 250 US, a fatty amido amine resin, to provide a range of viscosities, cure speeds and resistance properties.

Applications

- Maintenance coating applications
- Primers
- Enamel paint formulations

Features

- Excellent chemical resistance
- Excellent adhesion

Key Specified Properties

Property	Value	
Color, Gardner	8 max	
Viscosity (Brookfield) at 75 °C, cP	650 - 950 cP	
Amine value, mg KOH/g	330 - 360	

Typical Properties

Property	Value
AHEW	103
Density, lb/gal	8.1
Flash point (Seta)	>200°F

Advanced Materials Technical Datasheet



Processing

Mix ratio with 190 EEW liquid epoxy is 54 phr. Due to chemical reaction, Versamid[®] 125 and epoxy resins should not be mixed until just prior to use.

Typical Properties of a VERSAMID® 125 Cured Coating

Property	Value
Tack-free Time	5 hours
Through-cure time	12 hours
Pot Life	2 hours
Gel Time	129 minutes

*Cured with 190 EEW liquid epoxy resin

Typical Cured Resin Properties

84°C	
0.400 '	
6,100 psi	
5%	
239,000 psi	
8,500 psi	

*Cured with 190 EEW liquid epoxy resin for 7 days at 25° C

Typical Chemical Resistance Properties of Unfilled Castings

Chemical	% weight gain
10% Acetic acid	6.93%
10% Hydrochloric acid	0.80%
10% Sulfuric acid	1.24%
10% Sodium Hydroxide	0.57%
Methyl ethyl ketone	Destroyed
Xylene	15.47%
Ethanol	6.71%

*Percent weight gain after a 7-day cure at 25°C followed by a 21-day immersion at 25°C

Advanced Materials Technical Datasheet

General Purpose, White Gloss Enamel Formula, Room Temperature Cure

Part A	Pounds	Gallons
Mix the following materials:		
Epoxy resin solution	360.0	40.0
Xylene	36.0	5.0
Propylene glycol methyl ether acetate	40.2	5.0
Mix the following materials separate from Part A:		
Part B		
VERSAMID® 125 (mix prior to use)	121.5	15.0
Calcium Carbonate	150.0	6.6
TiO2	175.0	4.9
Bentonite clay agent	8.0	0.5
Xylene	108.0	15.0
Propylene glycol methyl ether	62.0	8.0
Total	1060.7	100.0

Thinners	Brush %	Spray %
MIBK	33	45
Xylene	33	
Toluene		50
Propylene glycol methyl ether	34	3
Dipropylene glycol methyl ether		2
Total	100	100

Formulation Attributes	
Viscosity, combined (Krebs)	71 KU
Weight per gallon, combined	10.6 lb/gal
Pigment:Binder ratio	1:1.2
PVC	21.8%
Solids	68.2%
Tack free (typical)	4-6 hours
Hard dry (typical)	Overnight
Full resistance properties (typical)	7 days



Storage

VERSAMID[®] **125** curing agent should be stored in a dry place, in its sealed original container, at temperatures between **2°C to 40°C (35.6°F to 104°F)**. Under these storage conditions the shelf life is **24 months** from date of manufacture. The product should not be exposed to direct sunlight.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up–to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to SDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Advanced Materials Technical Datasheet

Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas LLC, or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman, if any.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

VERSAMID[®] is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2021 Huntsman Advanced Materials Inc.

Main Offices:

Huntsman Corporation 10003 Woodloch Forest Dr The Woodlands, TX 77380 888-564-9318 Huntsman Advanced Technology Center 8600 Gosling Rd. The Woodlands, TX 77381 281-719-7400