

VERSAMID® 140 Polyamide Curing Agent

Product Description

VERSAMID® 140 Curing Agent is a medium to low viscosity, reactive polyamide designed for use with solid or liquid epoxy resins to provide tough, chemical-resistant thermoset coating applications that cure at room temperature. This curing agent is also useful in adhesive applications. VERSAMID® 140 curing agent and epoxy resin coating systems are more chemical and solvent resistant than VERSAMID® 115 systems and generally lower in viscosity than VERSAMID® 125 systems. It offers a unique combination of hardness and flexibility, along with the highest chemical and solvent resistance of the dimer-based polyamide resin series. All systems based on VERSAMID® 140 show good resistance against aliphatic hydrocarbons, lubricants, alkaline solutions and diluted acids: good to fair resistance against atmospheric agents and water.

Applications

- Chemical resistant coatings
- Adhesives
- Maintenance coating
- Primers
- High solids enamel paint formulations

Features

- Room temperature cure
- Combination of hardness and flexibility
- High chemical and solvent resistance
- FDA compliant*

Key Specified Properties

Property	Value
Appearance	Amber Liquid
Color, Gardner	7 max
Viscosity (Thermosel) at 25 °C, cP	8,000 – 12,000
Amine value, mg KOH/g	370 - 400

Typical Properties

Property	Value
Active Content	100%
Gardner Color	6
AHEW	97
Specific Gravity at 25 °C	0.97
Flash point	185°C

**Please use theoretical H-equivalent as indicative information in so far as the average H-equivalent could be significantly different due to the polymer development (molecular weight distribution) and the purity of commercial amines.*

These typical values should not be interpreted as specifications.

Processing

Mixing ratio suggestions are more reliable as being based on experimental tests. Due to chemical reaction, VERSAMID® 140 and epoxy resins should not be mixed until just prior to use.

Mixing Ratios	190 EEW liquid epoxy (50 – 70 phr)	475 EEW solid epoxy 40% NV (20 – 30 phr)
Pot Life, hours	2 hours	1-2 days
Max Exotherm peak	150°C	--
Tack Free Time, hours	6 hours (200um wet)	2 hours (200um wet)
Minimum application temperature	15°C	15°C

Storage

VERSAMID® 140 should be stored in a dry place, in its sealed original container, at temperatures between **2°C to 40°C (35.6°F to 104°F)**. Under these storage conditions the shelf life is **24 months** from date of manufacture. The product should not be exposed to direct sunlight.

Precautionary Statement

Huntsman Advanced Materials Americas LLC maintains up-to-date Safety Data Sheets (SDS) on all of its products. These sheets contain pertinent information that you may need to protect your employees and customers against any known health or safety hazards associated with our products. Users should review the latest MSDS to determine possible health hazards and appropriate precautions to implement prior to using this material.

First Aid!

Refer to SDS as mentioned above.

KEEP OUT OF REACH OF CHILDREN

FOR PROFESSIONAL AND INDUSTRIAL USE ONLY

Important Legal Notice

Sales of the product described herein ("Product") are subject to the general terms and conditions of sale of either Huntsman Advanced Materials LLC, or its appropriate affiliate including without limitation Huntsman Advanced Materials (Europe) BVBA, Huntsman Advanced Materials Americas LLC, or Huntsman Advanced Materials (Hong Kong) Ltd. ("Huntsman"). The following supercedes Buyer's documents.

Huntsman warrants that at the time and place of delivery all Products sold to Buyer shall conform to the specifications provided to Buyer by Huntsman, if any.

While the information and recommendations included in this publication are, to the best of Huntsman's knowledge, accurate as of the date of publication, NOTHING CONTAINED HEREIN (EXCEPT AS SET FORTH ABOVE REGARDING CONFORMANCE WITH SPECIFICATIONS PROVIDED TO BUYER BY HUNTSMAN) IS TO BE CONSTRUED AS A REPRESENTATION OR WARRANTY OF ANY KIND, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, NONINFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHTS, OR WARRANTIES AS TO QUALITY OR CORRESPONDENCE WITH PRIOR DESCRIPTION OR SAMPLE, AND THE BUYER ASSUMES ALL RISK AND LIABILITY WHATSOEVER RESULTING FROM THE USE OF SUCH PRODUCT, WHETHER USED SINGLY OR IN COMBINATION WITH OTHER SUBSTANCES.

No statements or recommendations made herein are to be construed as a representation about the suitability of any Product for the particular application of Buyer or user or as an inducement to infringe any patent or other intellectual property right. Buyer is responsible to determine the applicability of such information and recommendations and the suitability of any Product for its own particular purpose, and to ensure that its intended use of the Product does not infringe any intellectual property rights.

The Product may be or become hazardous. The Buyer should obtain Material Safety Data Sheets and Technical Data Sheets from Huntsman containing detailed information on Product hazards and toxicity, together with proper shipping, handling and storage procedures for the Product, and should comply with all applicable governmental laws, regulations and standards relating to the handling, use, storage, distribution and disposal of, and exposure to the Product. Buyer shall also take all steps necessary to adequately inform, warn and familiarize its employees, agents, direct and indirect customers and contractors who may handle or be exposed to the Product of all hazards pertaining to and proper procedures for safe handling, use, storage, transportation and disposal of and exposure to the Product, and the containers or equipment in which the Product may be handled, shipped or stored.

VERSAMID® is a registered trademark of Huntsman Corporation or an affiliate thereof in one or more, but not all countries.

© 2021 Huntsman Advanced Materials Inc.

Main Offices:

Huntsman Corporation
10003 Woodloch Forest Dr
The Woodlands, TX 77380
888-564-9318

Huntsman Advanced Technology Center
8600 Gosling Rd.
The Woodlands, TX 77381
281-719-7400